

## YIELD OF HOSTAPHAN® POLYESTER FILM

Thickness	Gauge	48	60	75	92	142	200	300	400	500	700
	Micron	12	15	19	23	36	51	76	102	127	178
Area Yield	In <sup>2</sup> /lb x 10 <sup>-3</sup>	41.3	33.1	26.5	21.6	14.0	9.9	6.6	5.0	4.0	2.8
	m <sup>2</sup> /kg	58.8	47.2	37.5	30.6	19.9	14.1	9.4	7.1	5.6	4.0
Basis Weight	Lb/ream	10.4	13.1	16.3	20.0	30.9	43.5	65.3	87.0	109	152

Thickness		PET Area Yield			
Gauge	Micron	Sq. in./lb.	Sq. ft./lb.	Sq. yd./lb.	m <sup>2</sup> /kg
1	0.25	1,980,198	13,751.4	1527.9	2816.5
48	12.19	41,254	286.5	31.8	58.7
60	15.24	33,003	229.2	25.5	46.9
75	19.05	26,403	183.4	20.4	37.6
92	23.37	21,524	149.5	16.6	30.6
142	36.07	13,945	96.8	10.8	19.8
200	50.80	9,901	68.8	7.6	14.1
300	76.20	6,601	45.8	5.1	9.4
400	101.60	4,901	34.4	3.8	7.0
500	127.00	3,960	27.5	3.1	5.6
700	177.80	2,829	19.6	2.2	4.0