



HOSTAPHAN®

Property	Thickness μm	Units	Value		Test Method	Test Conditions
			MD	TD		
OPTICAL						
Transparency	50	%	< 0.1		ASTM-D 1003-61 method A	-
Optical density	50	-	> 4		Internal method Similar to JIS K7605	-
PHYSICAL/CHEMICAL						
Density	50	g/cm^3	1.41		ASTM-D 1505-68 method C	23°C

MD = Machine direction, TD = Transverse direction

Delivery program Hostaphan® LHB

Thickness μm	Yield		Roll length <i>m</i>	Roll-diameter <i>mm</i>
	g/m^2	m^2/kg		
50	70.5	14.2	On request	On request

Core diameter: 152.4 mm (6")

The properties shown in this technical data sheet only apply to the film itself. We cannot guarantee the properties of an intermediate or final product made from or using the film. Instead, the intermediate or final product must be subjected to standard industrial testing.

This data sheet reflects our state of knowledge at the time this was prepared. The purpose is to provide an overview of the characteristics of our products and their potential uses. The values given reflect the typical characteristics of the film. They are not specification limits. They are neither a guarantee of specific properties nor the suitability of products in specific applications. The user must observe industrial property rights, such as patents or trademarks. The quality of our products is covered by the terms of the General Conditions of Sale of MITSUBISHI POLYESTER FILM GmbH.

Edition 07/16



Kasteler Str. 45 • 65203 Wiesbaden/Deutschland • Tel.: +49 611 96203 • Fax.: +49 611 9629357