



## Hostaphan® MUFK

### Matte, flame retardant and UV stable polyester film

Hostaphan® MUFK is a matte UV-resistant biaxially oriented film made of polyethylene terephthalate (PET) with a reduced flammability. The flame spread and total burning time of Hostaphan® MUFK is reduced compared with a standard PET film like Hostaphan® MP, MPK, MUV or MUVK, RN or RNK. Hostaphan® MUFK flammability is comparable to RUF but not as strongly reduced as Hostaphan® RF.

### Typical properties

| Property                             | Thickness<br>$\mu\text{m}$ | Units             | Value    |      | Test Method  | Test Conditions                            |
|--------------------------------------|----------------------------|-------------------|----------|------|--|--|
|                                      |                            |                   | MD       | TD   |  |  |
| <b>MECHANICAL</b>                    |                            |                   |          |      |  |  |
| Elongation at break                  | 15                         | %                 | 100      | 90   | ISO 527-1 and ISO 527-3<br>Sample type 2                               | Test speed 100 %/min.;<br>23 °C, 50 % r.h. |
| Young's Modulus                      | 15                         | N/mm <sup>2</sup> | 4500     | 5000 | ISO 527-1 and ISO 527-3<br>Sample type 2                               | Test speed 1 %/min.;<br>23 °C, 50 % r.h.   |
| <b>THERMAL</b>                       |                            |                   |          |      |  |  |
| Shrinkage                            | 15                         | %                 | 1.9      | 0.5  | DIN 40634  | 150°C, 15 min.                             |
| <b>OPTICAL</b>                       |                            |                   |          |      |  |  |
| Transparency                         | 15                         | %                 | 87       | < 20 | ASTM-D 1003-61<br>method A   | 400-700 nm<br>< 360 nm                     |
| Haze                                 | 15                         | %                 | 45       |      | ASTM-D 1003-61<br>method A   | Enlarged measurement<br>angle              |
| UV Transmission                      | 15                         | %                 | < 5      |      | Internal method<br>using lambda<br>3 spectrometer<br>from Perkin Elmer | 380 nm                                     |
| <b>SURFACE</b>                       |                            |                   |          |      |  |  |
| Gloss                                | 15                         | -                 | 15       |      | DIN 67530  | Measuring angle 20°                        |
| <b>FLAMMABILITY TESTING</b>          |                            |                   |          |      |  |  |
| Building materials<br>and components | 15                         | -                 | B2<br>B1 |      | DIN 4102-1   | Edge ignition                              |

MD = Machine direction, TD = Transverse direction



# HOSTAPHAN®

## Delivery program Hostaphan® MUFK

| Thickness<br>$\mu\text{m}$ | Yield                 |                        | Roll length<br>$\text{m}$ | Roll-diameter<br>$\text{mm}$ |
|----------------------------|-----------------------|------------------------|---------------------------|------------------------------|
|                            | $\text{g}/\text{m}^2$ | $\text{m}^2/\text{kg}$ |                           |                              |
| 15                         | 21                    | 48                     | On request                | On request                   |

Core diameter: 152.4 mm (6")

Disclaimer: Flammability and UV-resistance information given in this data sheet apply to the film only. The burning behaviour and UV-resistance of products made with/from Hostaphan® MUFK have to be tested regarding these properties under conditions relevant for the designated use.

This data sheet reflects our state of knowledge at the time this was prepared. The purpose is to provide an overview of the characteristics of our products and their potential uses. The values given reflect the typical characteristics of the film. They are not specification limits. They are neither a guarantee of specific properties nor the suitability of products in specific applications. The user must observe industrial property rights, such as patents or trademarks. The quality of our products is covered by the terms of the General Conditions of Sale of MITSUBISHI POLYESTER FILM GmbH.

Edition 07/23