



## Hostaphan® RNK 2SLK 23-36

### Transparent, siliconised polyester film for release liners

Hostaphan® RNK 2SLK is a one side silicone coated, biaxially oriented film, made of polyethylene terephthalate (PET) and characterized by outstanding properties. The siliconised film is designed to be used in release liner applications. Because the silicone is highly cured, there is essentially no migration of the silicone to any adhesive which may be in contact with the film. The film is not permitted to be used in food applications in the EU.

**WARNING:**

Silicone coated film is very slippery. Do not discard scrap film on the floor. Injury may result if stepped on.

### Typical properties

Property	Thickness µm	Units	Value		Test Method	Test Conditions
			MD	TD		
<b>MECHANICAL</b>						
Tensile strength	23 30 36	N/mm <sup>2</sup>	260 260 260	260 260 260	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 100 %/min.; 23 °C, 50 % r.h.
Elongation at break	23 30 36	%	140 140 140	130 130 130	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 100 %/min.; 23 °C, 50 % r.h.
Young's Modulus	23 30 36	N/mm <sup>2</sup>	4400 4500 4500	4600 4900 4900	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 1 %/min.; 23 °C, 50 % r.h.
F5-value (stress to obtain 5% elongation)	23 30 36	N/mm <sup>2</sup>	110 110 110	105 105 105	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 100 %/min.; 23 °C, 50 % r.h.
<b>THERMAL</b>						
Shrinkage	23-36	%	1.3	0.2	DIN 40634	150°C, 15 min.
<b>SURFACE</b>						
Coefficient of friction (uncoated surface) Static Dynamic	23-36	-		0.35 0.4	DIN53375 or ASTM-D 1894	-
<b>PHYSICAL/CHEMICAL</b>						
Density	23-36	g/cm <sup>3</sup>	1.4		ASTM-D 1505-68 method C	23°C
<b>SILICONE FUNCTIONALITY</b>						
Release from silicone side	23-36	g/25 mm	14		-	Unsupported T-peel from tesa 7475 tape @ 12in./min, initial value



Property	Thickness $\mu\text{m}$	Units	Value		Test Method	Test Conditions
			MD	TD		
The release force given in this datasheet has been measured using a standard commercial adhesive tape. In our experience, release levels vary with different pressure sensitive adhesives, face-stock materials and thickness as well as test conditions. Actual release force needs to be measured specifically for any given liner/adhesive/face-stock structure.						
Subsequent adhesion	23-36	%	> 90	-	-	Similar to FINAT FTM 11
Smear	23-36	-	None	-	-	Haze observed when rubbed once with index finger.
Rub-off	23-36	-	None	-	-	Coating removed when rubbed hard with index finger

MD = Machine direction, TD = Transverse direction

### Applications:

- Release liner for label stock
- Tapes
- Process liner
- Other release applications

### Delivery program Hostaphan® RNK 2SLK

Thickness $\mu\text{m}$	Yield		Roll length <i>m</i>	Roll-diameter <i>mm</i>
	$\text{g}/\text{m}^2$	$\text{m}^2/\text{kg}$		
23	32	31	On request	On request
30	42	24		
36	50	20		

Core diameter: 152.4 mm (6")

This data sheet reflects our state of knowledge at the time this was prepared. The purpose is to provide an overview of the characteristics of our products and their potential uses. The values given reflect the typical characteristics of the film. They are not specification limits. They are neither a guarantee of specific properties nor the suitability of products in specific applications. The user must observe industrial property rights, such as patents or trademarks. The quality of our products is covered by the terms of the General Conditions of Sale of MITSUBISHI POLYESTER FILM GmbH.