

HOSTAPHAN®

Hostaphan® RNK 2PRK

Transparent, siliconised polyester film for release liners

Hostaphan® RNK 2PRK is a one side silicone coated, biaxially oriented film, made of polyethylene terephthalate (PET) and characterized by outstanding properties. The siliconised film is designed to be used in release liner applications. Because the silicone is highly cured, there is essentially no migration of the silicone to any adhesive which may be in contact with the film. The film is not permitted to be used in food applications in the EU.

WARNING:

Silicone coated film is very slippery. Do not discard scrap film on the floor. Injury may result if stepped on.

Typical properties

Property	Thickness	Units	Value		Test Method	Test Conditions		
	μm		MD	TD				
MECHANICAL								
Tensile strength	19, 23 30	N/mm²	250 250	260 265	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 100 %/min.; 23 °C, 50 % r.h.		
Elongation at break	19, 23, 30	%	135	130	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 100 %/min.; 23 °C, 50 % r.h.		
Young's Modulus	19, 23 30	N/mm²	4400 4400	4800 4900	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 1 %/min.; 23 °C, 50 % r.h.		
F5-value (stress to obtain 5% elongation)	19, 23 30	N/mm²	110 110	100 105	ISO 527-1 and ISO 527-3 Sample type 2	Test speed 100 %/min.; 23 °C, 50 % r.h.		
THERMAL	THERMAL							
Shrinkage	19, 23 30	%	1.3 1.4	0.2 0.1	DIN 40634	150°C, 15 min.		
SURFACE				'				
Coefficient of friction (Uncoated surface) Static Dynamic	19, 23, 30	-	0.35 0.3		DIN53375 or ASTM-D 1894	-		
PHYSICAL/CHEMICA	AL							
Density	19, 23, 30	g/cm³	1.4		ASTM-D 1505-68 method C	23°C		
SILICONE FUNCTIONALITY								
Release from sili- cone side	19, 23, 30	g/25 mm	1	4	-	Unsupported T-peel from tesa 7475 tape @ 12in./min, initial value		



HOSTAPHAN®

Property	Thickness	Units	Value		Test Method	Test Conditions	
	μm		MD	TD			
The release force given in this datasheet has been measured using a standard commercial adhesive tape. In our experience, release levels vary with different pressure sensitive adhesives, face-stock materials and thickness as well as test conditions. Actual release force needs to be measured specifically for any given liner/adhesive/face-stock structure.							
Subsequent adhesion	19, 23, 30	%	> 9	90	-	Similar to FINAT FTM 11	
Smear	19, 23, 30	-	No	ne	-	Haze observed when rubbed once with index finger	
Rub-off	19, 23, 30	-	No	ne	-	Coating removed when rubbed hard with index finger	

MD = Machine direction, TD = Transverse direction

Applications:

- Release liner for label stock
- Other release applications

Delivery program Hostaphan® RNK 2PRK

Thickness	Yield		Roll length	Roll-
				diameter
μm	g/m²	m²/kg	m	mm
19	27	38	On request	On request
23	32	31		
30	42	24		

Core diameter: 152.4 mm (6")

This data sheet reflects our state of knowledge at the time this was prepared. The purpose is to provide an overview of the characteristics of our products and their potential uses. The values given reflect the typical characteristics of the film. They are not specification limits. They are neither a guarantee of specific properties nor the suitability of products in specific applications. The user must observe industrial property rights, such as patents or trademarks. The quality of our products is covered by the terms of the General Conditions of Sale of MITSUBISHI POLYESTER FILM GmbH.